

HumiSeal[®] 1A34 Urethane Conformal Coating

Technical Data Sheet

HumiSeal[®] 1A34 is a single component, fast curing polyurethane conformal coating. HumiSeal[®] 1A34 offers easy application and handling and fluoresces under UV light for ease of inspection. HumiSeal[®] 1A34 coating is MIL-I-46058C qualified, IPC-CC-830 and RoHS Directive 2002/95/EC compliant.

Properties of HumiSeal[®] 1A34

Density, per ASTM D1475	0.95 ± 0.02 g/cm ³
Solids Content, % by weight per Fed-Std-141, Meth. 4044	39 ± 2 %
Viscosity, per Fed-Std-141, Meth. 4287	125 ± 75 centipoise
VOC	576 grams/litre
Recommended Coating Thickness	25 - 75 microns
Drying Time to Handle per Fed-Std-141, Meth. 4061	120 ± 30 minutes
Recommended Curing Conditions	24 hrs @ RT or 4 hrs @ 76°C
Time Required to Reach Optimum Properties	7 days
Thinner, if needed (dipping, brushing, spraying)	HumiSeal [®] Thinner 521, 521EU
Recommended Stripper	HumiSeal [®] Stripper 1072
Shelf Life at Room Temperature, DOM	6 months
Thermal Shock, per MIL-I-46058C	-65°C to 125°C
Coefficient of Thermal Expansion - TMA	260 ppm/°C
Glass Transition Temperature - DSC	18°C
Modulus - DMA	51.3 MPa
Flammability, per MIL-I-46058C	Self-Extinguishing
Dielectric Withstand Voltage, per MIL-I-46058C	>1500 volts
Dielectric Constant, at 1MHz and 25°C per ASTM-D150-65T	3.5
Dissipation Factor, at 1MHz and 25°C per ASTM-D150-65T	0.028
Insulation Resistance, per MIL-I-46058C	1.7 x 10 ¹⁴ ohms (170TΩ)
Moisture Insulation Resistance, per MIL-I-46058C	6.3 x 10 ¹⁰ ohms (63GΩ)
Fungus Resistance, per ASTM G21	Passes

Application of HumiSeal[®] 1A34

Cleanliness of the substrate is of extreme importance for the successful application of a conformal coating. Surfaces must be free of moisture, dirt, wax, grease, flux residues and all other contaminants. Contamination under the coating could cause problems that may lead to assembly failures.

Dipping

Depending on the complexity, density and configuration of components on the assembly, it may be necessary to reduce the viscosity of HumiSeal[®] 1A34 with HumiSeal[®] Thinner 521 or 521EU in order to obtain a uniform film. Once optimum viscosity is determined, a controlled rate of immersion and withdrawal (5-15 cm/min) will further ensure even deposition of the coating and ultimately a uniform film. During the application, evaporation of solvent causes an increase in viscosity that should be adjusted by adding small amounts of HumiSeal[®] Thinner 521 or 521EU. Viscosity in the dip tank should be checked regularly using a simple measuring device such as a Zahn or Ford viscosity cup.

HumiSeal[®] 1A34 Technical Data Sheet

Spraying

HumiSeal[®] 1A34 can be sprayed using conventional spraying equipment. Spraying should be done in an environment with adequate ventilation so that the vapour and mist are carried away from the operator. The addition of HumiSeal[®] Thinner 521 or 521EU is necessary to ensure a uniform spray pattern resulting in pinhole-free film. The amount of thinner and spray pressure will depend on the specific type of spray equipment used and operator technique. The recommended ratio of HumiSeal[®] 1A34 to HumiSeal[®] Thinner 521 or 521EU is 1:1 by volume; however the ratio may need to be adjusted to obtain a uniform coating.

Brushing

HumiSeal[®] 1A34 may be brushed with a small addition of HumiSeal[®] Thinner 521 or 521EU. Uniformity of the film depends on component density and operator's technique.

Storage

HumiSeal[®] products may be stored at temperatures of 0 to 35°C. HumiSeal[®] 1A34 should be stored away from sunlight and excessive heat, in tightly closed containers. If coatings are partially used, the container should be purged with dry nitrogen prior to resealing. Prior to use, allow the product to equilibrate for 24 hours at a room temperature of 18 to 32°C.

Caution

Application of HumiSeal[®] Conformal Coatings should be carried out in accordance with local and National Health and Safety regulations.

The solvents in HumiSeal[®] Conformal Coatings are flammable. Material should not be used in presence of open flame or sparks. Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult MSDS/SDS prior to use.

Contact HumiSeal[®]

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.