

# 02GN089 Epoxy Quick Dry Primer


## TECHNICAL DATA SHEET

### Product Description

02GN089 is a high solids, corrosion, chemical and solvent resistant, military epoxy primer for use on the exterior of aircraft.

- Corrosion inhibiting
- Chemical and solvent resistant
- Resistant to hydraulic fluids, lubricating oils, phosphate ester based hydraulic fluids, Skydrol® hydraulic fluid and distilled water

### Components



#### **Mix ratio (by volume):**

- 020GN089 (base component) 3 parts
- 020GN089CAT (catalyst component) 1 part

### Specifications



02GN089 is qualified to:

- MIL-PRF-23377 Type I Class CI

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

#### **Product Compatibility:**

02GN089 is compatible with the following topcoat specifications:

- DMS 2115
- MIL-PRF-22750
- MIL-PRF-85285
- MMS 420

### Surface Preparation and Pretreatments



02GN089 primer can be applied over clean, dry, intact aluminum and composite surfaces. Aluminum surfaces shall be treated with materials conforming to MIL-C-5541 or equivalent.

# 02GN089 Epoxy Quick Dry Primer

## Instructions for Use



### Mixing Instructions:

Stir or shake the base component to ensure any pigment, which may have settled on the bottom of the can, has been fully incorporated into the base. Do not stir or shake the base component longer than 5 minutes. Slowly add the one volume of catalyst to three volumes base component. Mix by hand stirring, paint shaker or mechanical mixing to ensure the base/catalyst mixture is homogeneous. Do not shake or mechanically mix material for longer than 10 minutes. Constant agitation of the material during spray application is recommended.

*Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 13° and 35°C (55° to 95°F). The minimum temperature of the paint components should be 13°C (55°F) prior to mixing.*



### Induction Time:


Not required for standard dry time. Induction time of 30 minutes is recommended for applications requiring faster dry times, such as touch up or cold weather.



### Viscosity: (23°C/73°F)

- #4 Ford cup 40 seconds maximum

*Note: Viscosities quoted are the typical values obtained when using specified mix ratio.*



### Pot Life:

4 hours @ 21 - 25°C (70 - 77°F)

# 02GN089 Epoxy Quick Dry Primer

## Application Guidelines

### Recommended Application Conditions:

Temperature	15 - 30°C (59 - 86°F)
Relative Humidity	20 - 90%


### Application:

*These application guidelines represent PPG's best advice in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*



### Theoretical Coverage:

18 square meters/liter at 25 microns dry film (736 square feet/gallon at 1 mil dry film)  
 Recommended dry film thickness; 15 to 23 microns (0.6 to 0.9 mils)



### Dry Film Density:

1.46 grams/cubic centimeter (12.18 pounds/gallon)

### Dry Film Weight:

3.46 grams/square meter at 25 microns dry film (0.00762 pounds/square feet at 1 mil dry film)



### Equipment:

02GN089 is compatible with all current forms of spray equipment.

Equipment Type	Tip Size	Pot Pressure	Atomization Pressure at the Cap
Electrostatic Air Spray Gun	1.2 mm or 1.5 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)
Electrostatic Air Assisted Airless Spray Gun	#611 or #613 (Graco Nomenclature)	700 to 1200 psi (48 to 82 bar)	40 to 60 psi (2.8 to 4.1 bar)
High Volume Low Pressure Spray Gun (HVLP)	1.0 mm to 1.4 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.2 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

# 02GN089 Epoxy Quick Dry Primer

## Equipment Cleaning:

Clean spray equipment as soon as possible after use. Flush spray equipment with IS-237 (MIL-T-81772 Type II) or Desoclean™ 45 high performance solvent cleaner. Once material has cured, use an approved chemical paint removal system to strip primer from parts and equipment.

## Physical Properties (product)



**Color**            Dark Green



**Gloss**            Not Applicable



<b>Dry Times</b>	<b>21 - 27°C (70 - 80°F)</b>
Tack Free	2 - 3 hours maximum
Dry to Topcoat	3 - 4 hours maximum
Dry Hard	8 hours maximum
Full Cure	14 days maximum

*Note: Dry times above were established at room (ambient) temperatures, 75° ± 5°F and 50% ± 10% relative humidity. After 8 hours cure, it is recommended to solvent wipe the entire primed surface before top coating. After 24 hours of cure, it is recommended to scuff sand the entire primed surface for optimal inter-coat adhesion. Ref: T.O. 1-1-8 Section 6.12.6.5*

For dry to stack conditions only. Allow a minimum of 15 minutes flash off time at ambient temperatures prior to exposing painted parts to high temperatures. Complete testing should be done prior to use. Below are suggested starting points. Other variables may affect these cure schedules.

<b>Temperature</b>	<b>Time</b>
49°C (120°F)	45 minutes
60°C (140°F)	30 minutes
71°C (160°F)	20 minutes
82°C (180°F)	15 minutes

## 02GN089 Epoxy Quick Dry Primer

*Note: Ambient temperatures are defined as 70° ± 10°F and 50% ± 10% relative humidity.*



**VOC:**

Mixed, ready to use VOC (EPA method 24)	337 grams/liter
Base Component	405 grams/liter
Catalyst Component	190 grams/liter



**Flash Point closed cup:**

Base Component	8°C (46°F)
Catalyst Component	8°C (46°F)


**Shelf Life:**

12 months from date of manufacture for PRC-DeSoto Standard

*Note: Shelf life is provided for original, unopened containers.*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

### Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*



# 02GN089 Epoxy Quick Dry Primer

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200  
Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119  
Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666  
Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

#### **ASC – South Europe**

Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

Desoclean is trademark of PRC-DeSoto International, Inc. Skydrol is a trademark of Solutia, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc.  
12780 San Fernando Road  
Sylmar, CA 91342  
[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 5/16  
Lit: 4458